



How outdoor living should feel.

[Product Information](#)
[Design Center](#)
[Literature Center](#)
[Warranty & Care](#)
[Trade Professionals](#)
[Company Information](#)
SEARCH: 

Trade Professionals

TrexConnect™ Login

Technical Info

Properties

Evaluation Reports

MSDS

Usage Guidelines

Technical Bulletins

Safety Info

TrexPro® Program

Material Suppliers

FAQs

Request Information

Home

Trade Professionals

PHYSICAL AND MECHANICAL PROPERTIES

Property	Test Method	Value							
Abrasion Resistance	ASTM D2394	.01 wear/1000 revs.							
Hardness	ASTM D143	1124 lbs.							
Self Ignition Temperature	ASTM D1929	743°F							
Flash Ignition Temperature	ASTM D1929	698°F							
Flame Spread (a)	ASTM E84	80							
Water Absorption (sanded surface) 24 hr. immersion	ASTM D1037	4.3%							
Water Absorption (unsanded surface) 24 hr. immersion	ASTM D1037	1.7%							
Expansion/Contraction Properties (b)									
<p>Thermal Typical Trex Wood Polymer® lumber values for Coefficient of Thermal Expansion/Contraction (36" long samples) Width: 35.2×10^{-6} to 42.7×10^{-6} (inch/inch/°F) Length: 16.1×10^{-6} to 19.2×10^{-6} (inch/inch/°F)</p> <p>Moisture: Typical Trex Wood Polymer lumber values for</p> <table style="width: 100%; border: none;"> <tr> <td style="text-align: center;">Long Term Water Immersion</td> <td style="text-align: center;">Constant High Humidity</td> </tr> <tr> <td style="text-align: center;">36" long samples:</td> <td style="text-align: center;">6" long samples:</td> </tr> <tr> <td style="text-align: center;">Width ~3%</td> <td style="text-align: center;">Width ~1%</td> </tr> </table>				Long Term Water Immersion	Constant High Humidity	36" long samples:	6" long samples:	Width ~3%	Width ~1%
Long Term Water Immersion	Constant High Humidity								
36" long samples:	6" long samples:								
Width ~3%	Width ~1%								
Nail Withdrawal (c)	ASTM D1761	163 lbs/in							
Screw Withdrawal (c)	ASTM D1761	558 lbs/in							
Static Coefficient of Friction – Dry (d)	ASTM D2047	0.53/0.55							
Static Coefficient of Friction – Dry (d)	ASTM F1679	0.59/0.70							
Static Coefficient of Friction – Wet (d)	ASTM F1679	0.70/0.75							
Fungus Resistance (White & Brown Rot)	ASTM D1413	rating = No Decay							
Termite Resistance (e)	AWPAE1-72	rating = 9.6							
Specific Gravity (typical)	ASTM D2395	0.91 to 0.95							
		Ultimate (typical) Values	Design Values						
Compression Parallel (f)(g)	ASTM D198	1806 psi	550 psi						
Compression Perpendicular (f)(h)	ASTM D143	1944 psi	625 psi						
Tensile Strength (f)	ASTM D198	854 psi	250 psi						
Shear Strength (f)	ASTM D143	561 psi	200 psi						
Modulus of Rupture (f)	ASTM D4761	1423 psi	250 psi						
Modulus of Elasticity (f)	ASTM D4761	175,000 psi	100,000 psi						
Thermal Conductivity	ASTM C177	1.57 BTU-in/hr-ft @85°F							
Leachate (i)	TCLP-EPA 1311	pass							

Notes:

(a) Corresponding Smoke Developed Index is 285.

(b) **Values shown are for reference only.** These values should not be used to calculate gapping for *Trex Wood-Polymer* lumber. Follow *Trex Wood-Polymer* lumber installation literature for proper width-to-width and end to end gapping information.

(c) 8d common wire nail. No. 10 wood screw.

(d) ASTM D2047 test conducted on sanded/unsanded unweathered samples with leather surface. ASTM F1679 test conducted on sanded/unsanded weathered samples with neolite surface.

(e) Material weight loss was 0%.

(f) Ultimate strength values are not meant for design analysis. Testing performed on a 2x6 cross section. Design values are for temperatures up to 130°F.

(g) Compressive strength parallel to the length.

(h) Compressive strength perpendicular to length.

(i) Leaching was below levels established by EPA for all constituent categories.

[Career Center](#) [Contact Us](#) [Find a Contractor](#) [Site Map](#)
© Copyright 1997-2007 Trex Company, Inc. All rights reserved. [Privacy Policy](#) [Terms of Use](#)